



# RUBBER PRODUCTS DISTRIBUTORS

317-898-2511  
Fax # 317-898-0772

## Natural Rubber

Common Name _____	Natural Rubber
Trade Names _____	Micro
	Qualatex
	Duro
	Amtext
ASTM D-2000 Classification _____	AA
Military (MIL-STD 417) _____	RN
Chemical Definition _____	Polyisoprene

### GENERAL CHARACTERISTICS

Durometer Range (Shore A) _____	20 – 100
Tensile Range (P.S.I.) _____	500 – 3500
Elongation (Max.%) _____	700
Compression Set _____	Excellent
Resilience – Rebound _____	Excellent
Abrasion Resistance _____	Excellent
Tear Resistance _____	Excellent
Solvent Resistance _____	Poor
Oil Resistance _____	Poor
Low Temperature Usage (F°) _____	-20° to -60°
High Temperature Usage (F°) _____	to 175°
Aging Weather – Sunlight _____	Poor
Adhesion to Metals _____	Excellent

### COMMENT

Natural Rubber has many good characteristics. It has high resilience, good compression set, good roll building behavior, and molding properties; very good friction surface, but not a fine smooth surface when ground; high tear strength, low crack growth; usable for ketones and alcohol; and good low temperature properties.

Natural Rubber is not recommended for oil and solvent resistance and ozone attacks it.

Mailing Address:  
P.O. Box 19404  
Indianapolis, IN 46219  
04/02/03

E-mail: [rpdsales@rubbergrommets.com](mailto:rpdsales@rubbergrommets.com)  
Website: [www.rubbergrommets.com](http://www.rubbergrommets.com)

Shipping Address:  
2725 Tobey Drive  
Indianapolis, IN 46219  
Revision: 1